



# Standard Specification for Medium-Hard-Drawn Copper Wire<sup>1</sup>

This standard is issued under the fixed designation B 2; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification covers medium-hard-drawn round copper wire for electrical purposes (see Explanatory Note 1).

1.2 The SI values of density and resistivity are to be regarded as standard. For all other properties the inch-pound values are to be regarded as standard, and the SI units may be approximate.

## 2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

### 2.2 ASTM Standards:

B 5 Specification for Electrolytic Tough-Pitch Copper Refinery Shapes<sup>2</sup>

B 49 Specification for Copper Redraw Rod for Electrical Purposes<sup>2</sup>

B 170 Specification for Oxygen-Free Electrolytic Copper—Refinery Shapes<sup>2</sup>

B 193 Test Method for Resistivity of Electrical Conductor Materials<sup>3</sup>

B 258 Specification for Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors<sup>3</sup>

### 2.3 Other Document:

*NBS Handbook 100—Copper Wire Tables of the National Bureau of Standards<sup>4</sup>*

## 3. Ordering Information

3.1 Orders for material under this specification should include the following information:

3.1.1 Quantity of each size,

3.1.2 Wire size: diameter in inches (see 5.1 and Table 1),

3.1.3 Type of copper, if special (see Section 4),

3.1.4 Package size (see 10.1),

3.1.5 Special package marking, if required, and

3.1.6 Place of inspection (Section 10).

## 4. Materials and Manufacture

4.1 The material shall be copper of such quality and purity that the finished product shall have the properties and characteristics prescribed in this specification.

NOTE 1—Specifications B 5, B 49, and B 170 define the materials suitable for use.

4.2 Copper bars of special qualities, forms, or types, as may be agreed upon between the manufacturer and the purchaser, and which will conform to the requirements prescribed in this specification, may also be used.

## 5. Dimensions and Permissible Variations

5.1 The wire sizes shall be expressed as the diameter of the wire in decimal fractions of an inch to the nearest 0.0001 in. (0.1 mil) or in millimetres to the nearest 0.001 mm (Explanatory Note 2).

5.2 Within the range of diameters included in Table 1 the wire shall not vary from the specified diameter by more than  $\pm 1\%$ , expressed to the nearest 0.0001 in. (0.1 mil) 0.001 mm.

5.3 Ten percent, but not less than five coils or spools (or all if the lot is less than five) from any lot of wire shall be gaged at three places. If accessible, one gaging shall be taken near each end and one near the middle. If any of the selected coils or spools fails to conform to the requirements prescribed in 5.2, all coils or spools shall be gaged in the manner specified.

## 6. Workmanship, Finish, and Appearance

6.1 The wire shall be free from all imperfections not consistent with the best commercial practice.

## 7. Tensile Properties

7.1 The wire shall conform to the requirements as to tensile properties prescribed in Table 1 (Explanatory Note 2 and Note 3).

7.2 Tests on a specimen containing a joint shall show at least 95 % of the minimum tensile strength given in Table 1. Elongation tests shall not be made on a specimen containing a joint.

7.3 For wire the nominal diameter of which is more than 0.001 in. (1 mil) (0.025 mm) greater than a size listed in Table

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B-1 on Electrical Conductors and is the direct responsibility of Subcommittee B01.04 on Conductors of Copper and Copper Alloys.

Current edition approved April 10, 2000. Published June 2000. Originally published as B 2 – 12. Last previous edition B 2 – 94.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 02.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 02.03.

<sup>4</sup> Available from the National Technical Information Service, 5285 Port Royal Rd., Springfield, VA 22161.

**TABLE 1 Tensile Requirements**

Diameter		Area at 20°C			Tensile Strength				Elongation, min, %in 10-in. (250 mm)
in.	mm	cmil	in. <sup>2</sup>	mm <sup>2</sup>	psi		MPa		
					Min	Max	Min	Max	
0.4600	11.684	211 600	0.1662	107.0	42 000	49 000	290	340	3.8
0.4096	10.404	167 800	0.1318	85.0	43 000	50 000	295	345	3.6
0.3648	9.266	133 100	0.1045	67.4	44 000	51 000	305	350	3.2
0.3249	8.252	105 600	0.08291	53.5	45 000	52 000	310	360	3.0
0.2893	7.348	83 690	0.06573	42.4	46 000	53 000	315	365	2.8
0.2576	6.543	66 360	0.05212	33.6	47 000	54 000	325	370	2.5
0.2294	5.827	52 620	0.04133	26.7	48 000	55 000	330	380	2.2
0.2043	5.189	41 740	0.03278	21.2	48 330	55 330	335	380	1.9
0.1819	4.620	33 090	0.02599	16.8	48 660	55 660	335	385	1.7
0.1620	4.115	26 240	0.02061	13.3	49 000	56 000	340	385	1.5
0.1443	3.665	20 820	0.01635	10.5	49 330	56 330	340	390	1.4
0.1285	3.264	16 510	0.01297	8.37	49 660	56 660	340	390	1.3
0.1144	2.906	13 090	0.01028	6.63	50 000	57 000	345	395	1.3
0.1019	2.588	10 380	0.008155	5.26	50 330	57 330	345	395	1.2
0.0907	2.304	8 230	0.00646	4.17	50 660	57 660	350	400	1.2
0.0808	2.052	6 530	0.00513	3.31	51 000	58 000	350	400	1.1
0.0720	1.829	5 180	0.00407	2.63	51 330	58 330	355	400	1.1
0.0641	1.628	4 110	0.00323	2.08	51 660	58 660	355	405	1.0
0.0571	1.450	3 260	0.00256	1.65	52 000	59 000	360	405	1.0
0.0508	1.290	2 580	0.00203	1.31	52 330	59 330	360	410	1.0
0.0453	1.151	2 050	0.00161	1.04	52 660	59 660	365	410	1.0
0.0403	1.024	1 620	0.00128	0.823	53 000	60 000	365	415	1.0

1, but which is less than that of the next larger size, the requirements of the next larger size shall apply.

7.4 Determine the elongation of the wire as the permanent increase in length due to the breaking of the wire in tension, measured between gage marks placed originally 10 in. (254 mm) apart upon the test specimen (Explanatory Note 4).

7.5 If any part of the fracture takes place outside the gage marks or in the jaws of the testing machine, or if an examination of the specimen indicates a flaw, the value obtained may not be representative of the material. In such cases the test may be discarded and a new test made.

7.6 *Retests*—If, upon testing a sample from any coil or spool of wire, the results do not conform to the requirements prescribed in Table 1, two additional samples shall be tested and the average of the three tests shall determine the acceptance or rejection of the coil or spool.

## 8. Resistivity

8.1 Electrical resistivity shall be determined on representative samples by resistance measurements (Explanatory Note 5 and Note 6). At a temperature of 20°C the resistivity shall not exceed the following values:

Nominal Diameter, in.	Resistivity at 20°C,	
	Ω-lb/mile <sup>2</sup>	Ω-g/m <sup>2</sup>
0.460 to 0.325 (11.684 to 8.255 mm), incl	896.15	0.15695
Under 0.325 to 0.0403 (8.255 to 1.024 mm), incl	905.44	0.15858

8.2 Tests to determine conformance to the electrical resistance requirements shall be made in accordance with Test Method B 193.

## 9. Joints

9.1 No joints shall be made in the completed wire (Explanatory Note 7). Joints in wire and rods, prior to final drawing, shall be made in accordance with the best commercial practice and shall conform to the requirements prescribed in 7.2.

## 10. Inspection

10.1 Unless otherwise specified in the contract or purchase

order, the manufacturer shall be responsible for the performance of all inspection and test requirements specified (Explanatory Note 8).

10.2 All inspections and tests shall be made at the place of manufacture unless otherwise especially agreed to between the manufacturer and the purchaser at the time of the purchase.

10.3 The manufacturer shall afford the inspector representing the purchaser all reasonable manufacturer's facilities to satisfy that the material is being furnished in accordance with this specification.

10.4 Unless otherwise agreed upon between the purchaser and the manufacturer, conformance of the wire to the various requirements listed in this specification shall be determined on samples taken from each lot of wire presented for acceptance.

10.5 The manufacturer shall, if requested prior to inspection, certify that all wire in the lot was made under such conditions that the product as a whole conforms to the requirements of this specification as determined by regularly made and recorded tests.

### 10.6 *Inspection and Testing Terms:*

10.6.1 *Lot*—A lot is any amount of wire of one type and size presented for acceptance at one time; such amount, however, not to exceed 100 000 lb or 45 000 kg (Explanatory Note 9).

10.6.2 *Sample*—A sample is a quantity of production units (coils, reels, etc.) selected at random from the lot for the purpose of determining conformance of the lot to the requirements of this specification.

10.6.3 *Specimen*—A specimen is a length of wire removed for test purposes from any individual production unit of the sample.

10.7 *Sample Size*—The number of production units in a sample (Explanatory Note 8) shall be as follows:

10.7.1 For tension, elongation, and resistivity determinations, the sample shall consist of four production units. From each unit, one test specimen of sufficient length shall be removed for the performance of the required tests.

**TABLE 2 Sampling for Dimensional Measurements**

Number of Units in Lot	First Sample		Second Sample		
	Number of Units in Sample, $n_1$	Allowable Number of Defects in First Sample, $c_1$	Number of Units in Sample, $n_2$	$n_1$ plus $n_2$	Allowable Number of Defects in Both Samples, $c_2$
1 to 14, incl	all	0	...	...	...
15 to 50, incl	14	0	...	...	...
51 to 100, incl	19	0	23	42	1
101 to 200, incl	24	0	46	70	2
201 to 400, incl	29	0	76	105	3
401 to 800, incl	33	0	112	145	4
Over 800	34	0	116	150	4

10.7.2 For dimensional measurements, the sample shall consist of a quantity of production units shown in Table 2 under the heading “First Sample.”

10.7.3 For surface-finish inspection and for packaging inspection (when specified by the purchaser at the time of placing the order) the sample shall consist of a quantity of production units shown in Table 3.

## 11. Packaging and Shipping

11.1 Package sizes shall be agreed upon between the manufacturer and the purchaser in the placing of individual orders.

11.2 The wire shall be protected against damage in ordinary handling and shipping.

**TABLE 3 Sampling for Surface Finish and Packaging Inspection**

Number of Units in Lot	Number of Units in Sample, $n$	Allowable Number of Defective Units, $c$
1 to 30, incl	all	0
31 to 50, incl	30	0
51 to 100, incl	37	0
101 to 200, incl	40	0
201 to 300, incl	70	1
301 to 500, incl	100	2
501 to 800, incl	130	3
Over 800	155	4

## 12. Keywords

12.1 copper wire; medium-hard copper wire; round copper electrical wire; round copper wire

## EXPLANATORY NOTES

NOTE 1—Medium-hard drawn wire approaches hard-drawn wire in its characteristics, but from the very nature of the product, exact uniformity in tensile strength cannot be obtained. Hence it has been necessary to establish a range of tensile strengths within which standard medium-hard-drawn wire may be expected to be found.

NOTE 2—The values of the wire diameters in Table 1 are given to the nearest 0.0001 in. (0.001 mm) and correspond to the standard sizes given in Specification B 258. The use of gage numbers to specify wire sizes is not recognized in this specification because of the possibility of confusion. An excellent discussion of wire gages and related subjects is contained in *NBS Handbook 100*.

NOTE 3—Other tests than those provided in this specification have been considered at various times, such as twist tests, wrap tests, tests for elastic limit, etc. It is the opinion of the committee that twist and wrap tests on medium-hard-drawn wire do not serve a useful purpose and should be regarded as undesirable, as well as inconclusive as to results and significance. Tests for values of elastic limit are likewise indefinite as to results. Tests to determine elastic properties of medium-hard-drawn wire from which wire stringing and sagging data may be compiled are considered to be outside the scope of the acceptance tests contemplated in this specification.

NOTE 4—It is known that the rate of loading during tension testing of copper affects the performance of the sample to a greater or lesser extent, depending upon many factors. In general, tested values of tensile strength are increased and tested values of elongation are reduced with increase of speed of the moving head of the testing machine. These effects are pronounced when the speed of the moving head is excessive in the testing of medium-hard-drawn wires. It is suggested that tests be made at speeds of moving head that, under no-load conditions, are not greater than 3 in. (75 mm)/min, but in no case at a speed greater than that at which correct readings can be made.

NOTE 5—“Resistivity” is used in place of “percentage conductivity.” The value of 0.15328 $\Omega \cdot \text{g}/\text{m}^2$  at 20°C is the international standard for the

resistivity of annealed copper equal to 100 % conductivity. This term means that a wire 1 m in length and weighing 1 g would have a resistance of 0.15328  $\Omega$ . This is equivalent to a resistivity value of 875.20  $\Omega \cdot \text{lb}/\text{mile}^2$ , which signifies the resistance of a wire 1 mile in length weighing 1 lb. It is also equivalent, for example, to 1.7241  $\mu\Omega/\text{cm}$  of length of a bar 1  $\text{cm}^2$  in cross section. A complete discussion of this subject is contained in *NBS Handbook 100*. Relationships that may be useful in connection with the values of resistivity prescribed in this specification are as in Table 4, each column containing equivalent expressions, at 20°C.

NOTE 6—The value of density of copper is in accordance with the International Annealed Copper Standard. The corresponding value at 0°C is 8.90  $\text{g}/\text{cm}^3$  (0.32150  $\text{lb}/\text{in.}^3$ ). As pointed out in the discussion of this subject in *NBS Handbook 100*, there is no appreciable difference in values of density of medium-hard-drawn and annealed copper wire.

NOTE 7—Mechanical joints made during inspection at the request of the purchaser are permissible if agreed upon at the time of placing the order.

NOTE 8—Cumulative results secured on the product of a single manufacturer, indicating continued conformance to the criteria, are necessary to ensure an over-all product meeting the requirements of this specification. The sample sizes and conformance criteria given for the various characteristics are applicable only to lots produced under these conditions.

**TABLE 4 Resistivity Relationships**

Conductivity at 20°C, %	100.00	97.66	96.66
$\Omega \cdot \text{lb}/\text{mile}^2$	875.20	896.15	905.44
$\Omega \cdot \text{g}/\text{m}^2$	0.15328	0.15694	0.15857
$\Omega \cdot \text{cmil}/\text{ft}$	10.371	10.619	10.729
$\Omega \cdot \text{mm}^2/\text{m}$	0.017241	0.017654	0.017837
$\mu\Omega \cdot \text{in.}$	0.67879	0.69504	0.70224
$\mu\Omega \cdot \text{cm}$	1.7241	1.7654	1.7837

NOTE 9—A lot should comprise material taken from a product regularly meeting the requirements of this specification. Inspection of individual lots of less than 5000 lb or 2270 kg of wire cannot be justified

economically. For small lots of 5000 lb or less, or 2270 kg or less, the purchaser may agree to the manufacturer's regular inspection of the product as a whole as evidence of acceptability of such small lots.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*